

XV6841-569

●Characteristics

XV6841-569 is a UV curable Glass attaching paste.

●Caution

Please store the material in a freezer below -20°C .

Keep syringes for 1 to 2 hours at room temperature before using.

●Standard Curing Condition

2000mJ/cm²

●Property

item	unit	XV6841-569	note
Viscosity	Pa·s	17.0	HBT 50rpm
Thixotropic Index	—	3.5	HBT 5rpm/50rpm
C.T.E.	α 1	ppm	TMA
	α 2	ppm	
Tensile Modulus	GPa	0.5	DMA
Tg	$^{\circ}\text{C}$	35	