

Thermal Interface - Wet Dispensed

Dow Corning® 1-4173 Thermally Conductive Adhesive

1-part gray, flowable thermally conductive adhesive with high tensile strength

FEATURES

- Flowable
- Heat Cure
- Outstanding thermal conductivity values
- High tensile strength
- No added solvents

BENEFITS

- No mixing of separate components required
- Rapid, versatile cure processing controlled by temperature
- Able to flow, fill or self-leveling after dispensing
- Heat flow away from electronic components can increase reliability

POTENTIAL USES

- Bonding integrated circuit substrates
Adhering lids and housings
- Base plate attach
- Heat sink attach

APPLICATION METHODS

- Automated or manual dispensing

TYPICAL PROPERTIES

Specification Writers: Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

Property	Unit	Value
Viscosity	cP	61300
	mPa-sec	61300
	Pa-sec	61.3
Thixotropy	NA	3.8
Specific Gravity (Cured)	-	2.7
Thermal Conductivity	btu/hr ft degF	1.098
	W/mK	1.9
Heat Cure Time @ 100°C	minutes	90
Heat Cure Time @ 125°C	minutes	30
Heat Cure Time @ 150°C	minutes	20
Durometer Shore A	-	92
Unprimed Adhesion - Lap Shear (Al)	psi	650
	MPa	4.5
	kg/cm ²	45
Linear CTE (by TMA)	ppm/°C	125
Shelf Life at 5°C	months	6

DESCRIPTION

The heat-cure, thermally conductive adhesives produce no by-products in the cure process, allowing their use in deep section and complete confinement. These adhesives will develop good, primerless adhesion to a variety of common substrates including metals, ceramics, epoxy laminate boards, reactive materials and filled plastics. Long-term, reliable protection of sensitive circuits and components is important in many of today's delicate and demanding electronic applications. With the increase in processing power and the trend toward smaller, more compact electronic modules, the need for thermal management is growing. Thermally conductive silicones function as heat transfer media, durable dielectric insulation, barriers against environmental contaminants and as stress-relieving shock and vibration absorbers over a wide temperature and humidity range. In addition to sustaining their physical and electrical properties over a broad range of operating conditions, silicones are resistant to ozone and ultraviolet degradation and have good chemical stability. Good heat transfer is dependent on a good interface between the heat producing device and the heat transfer media. Silicones have a low surface tension that enables them to wet most surfaces, which can lower the thermal contact resistance between the substrate and the material.

SUBSTRATE TESTING

To ensure maximum bond strength for adhesives on a particular substrate, 100 percent cohesive failure of the adhesive in a lap shear or similar adhesive strength test is needed. This ensures compatibility of the adhesive with the substrate being considered. Also, this test can be used to determine minimum cure time or to detect the presence of surface contaminants such as mold release agents, oils, greases and oxide films.

PROCESSING/CURING

Addition-cure adhesives should be cured at 100°C (212 °F) or above. The cure rate is rapidly accelerated with heat (see heat-cure times in Typical Properties table). Thin sections of less than mils may be cured in 15 minutes at 150°C (30 °F). For thicker sections, a pre-cure at 70°C (158°F) may be necessary to reduce voids in the elastomer. Length of pre-cure will depend on section thickness and confinement of adhesive. It is recommended that 30 minutes at 70°C (158°F) be used as a starting point for determining necessary pre-cure time. Addition-curing materials contain all the ingredients needed for cure with no by-products from the cure mechanism. Deep-section or confined cures are possible. Cure progresses evenly throughout the material. These adhesives generally have long working times.

ADHESION

Dow Corning silicone adhesives are specially formulated to provide unprimed adhesion to many reactive metals, ceramics and glass, as well as to selected laminates, resins and plastics. However, good adhesion cannot be expected on non-reactive metal substrates or non-reactive plastic surfaces such as Teflon®, polyethylene or polypropylene. Special surface treatments such as chemical etching or plasma treatment can sometimes provide a reactive surface and promote adhesion to these types of substrates. Dow Corning® brand primers can be used to increase the chemical activity on difficult substrates. For best results, the primer should be applied in a very thin, uniform coating and then wiped off after application. After application, primers should be thoroughly cured prior to application of the silicone elastomer. Poor adhesion can be experienced on plastic or rubber substrates that are highly plasticized, since the mobile plasticizers act as release agents. Small-scale laboratory evaluation of all substrates is recommended before production trials are made. In general, increasing the cure temperature

and/or cure time will improve the ultimate adhesion.

USEFUL TEMPERATURE RANGES

For most uses, silicone adhesives should be operational over a temperature range of -45 to 200°C (-49 to 392 °F) for long periods of time. However, at both the low and high temperature ends of the spectrum, behavior of the materials and performance in particular applications can become more complex and require additional considerations. For low-temperature performance, thermal cycling to conditions such as -55°C (-67°F) may be possible for most products, but performance should be verified for your parts or assemblies. Factors that may influence performance are configuration and stress sensitivity of components, cooling rates and hold times, and prior temperature history. At the high-temperature end, the durability of the cured silicones is time and temperature dependent. As expected, the higher the temperature, the shorter the time the material will remain useable.

SOLVENT EXPOSURE

Although highly filled silicones such as those discussed in this data sheet are generally more resistant to solvent or fuel exposure, standard silicones are intended only to survive splash or intermittent exposures. Testing should be done to confirm performance of the adhesives in the application and under the specified environmental conditions.

STORAGE AND SHELF LIFE

Shelf life is indicated by the "Use By" date found on the product label. For best results, Dow Corning thermally conductive materials should be stored at or below the maximum specified storage temperature. Special precautions must be taken to prevent moisture from contacting these materials. Containers should be kept tightly closed and head or air space

minimized. Partially filled containers should be purged with dry air or other gases, such as nitrogen. Any special storage and handling instructions will be printed on the product containers.

HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area. For further information, please see our website, www.dowcorning.com, or consult your local Dow Corning representative.

LIMITATIONS

These products are neither tested nor represented as suitable for medical or pharmaceutical uses.

LIMITED WARRANTY INFORMATION PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this

information should not be used in substitution for customer's tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent. Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. **DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**

SAFE HANDLING INFORMATION

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE,

PHYSICAL AND HEALTH HAZARD INFORMATION. THE MATERIAL SAFETY DATA SHEET IS AVAILABLE ON THE DOW CORNING WEBSITE AT WWW.DOWCORNING.COM, OR FROM YOUR DOW CORNING REPRESENTATIVE, OR DISTRIBUTOR, OR BY CALLING YOUR GLOBAL DOW CORNING CONNECTION.

For More Information

To learn more about these and other products available from Dow Corning, please visit the Dow Corning Electronics website at www.dowcorning.com/electronics.



Electronics
Solutions

Dow Corning and Sylgard are registered trademarks of Dow Corning Corporation. All other trademarks or brand names are the property of their respective owners. ©2008 Dow Corning Corporation. All rights reserved. Printed in USA Form No. 11-1322B-01